

Heavy Slack Wax

H8

Properties	Result	Test Method
Oil Content %	5-8	ASTM D-721
Congealing Point °C	62	ASTM D-938
Flash point °C	240	ASTM D-92
Kinematic Viscosity at 100 °C	5.5-7.5	ASTM D-7042
Density at 15.6 °C kg/m ³	0.81-0.84	ASTM D-4052
Color @70 °C (Max)	3	ASTM D-1500

Application

Production of waterproof fabrics

Candle factories & blending components

Various industries

Production of all types of coatings

Matchmaking, composition and insulation

Inks, matches, polishes, carbon paper, & can be applied externally as good dust suppressants or controlled-release agents for various chemical and Fertilizers.

Packing

Drum 175 kg